



CONSTRUCTION	Tufting 1/10" saxony
STRUCTURE	Tufté 1/10" saxony
STRUKTUR	Getuftet 1/10" saxony
STRUCTUUR	Getuft 1/10" saxony
PILE MATERIAL	100% PA 6 IMPREL®
COMPOSITION DU VELOURS	
POLMATERIAL	
POOLMATERIAAL	
PRIMARY BACKING	Non woven PES
SUPPORT	Non tissé
TRÄGERMATERIAL	Vlies
TUFTDOEK	Felt
SECONDARY BACKING	Action Back
DOSSIER	
RÜCKEN	
TAPIJTRUG	
PILE WEIGHT	Ca. 900 gr/m ²
POIDS DU VELOURS	
POLEINSATZGEWICHT	
POOLGEWICHT	
TOTAL WEIGHT	Ca. 1.875 gr/m ²
POIDS TOTAL	
GESAMTGEWICHT	
TOTAAL GEWICHT	
PILE HEIGHT	Ca. 4 mm
EPAISSEUR DU VELOURS	
POLHÖHE	
POOLHOOGTE	
TOTAL HEIGHT	Ca. 7 mm
EPAISSEUR TOTAL	
GESAMTHÖHE	
TOTALE DIKTE	
TUFT DENSITY	Ca. 170 000/m ²
NOMBRES DE POINTS	
NOPPENZAHL	
AANTAL PUNTEN	
PILE DENSITY	Ca. 0.143 g/cm ³
DENSITÉ DU VELOURS	
POLROHDICHTÉ	
POOLDICHTHEID	
CLASSIFICATION	EN 1307
CLASSEMENT	32 - LC2
KLASSIFIKATION	
CLASSIFICATIE	
UPEC	U3 P3 E1 C0
	Certification CSTB: 10/276
CASTOR CHAIR SUITABILITY	EN 985
CHAISE À ROULETTES	A: intensive use
STUHLROLLENEIGNUNG	
ROLSTOELGESCHIKTHEID	
STAIR SUITABILITY	EN 1963
ESCALIERS	A: intensive use
TREPPENEIGNUNG	
TRAPPENGESCHIKTHEID	


PERMANENTLY ANTISTATIC	ISO 6356
ANTISTATIQUE PERMANENT	≤ 2 kV
PERMANENT ANTISTATISCH	
PERMANENT ANTISTATISCH	
IMPACT NOISE RATING	ISO 140-8
ISOLATION PHONIQUE	24 dB ΔLw
TRITTSCHALLVERBESSERUNG	
GELUIDSISOLATIE	
SOUND ABSORPTION	ISO 354
ABSORPTION PHONIQUE	0.20 αw
SCHALLABSORPTIONSGRAD	
GELUIDSABSORPTIE	
THERMAL RESISTANCE	ISO 8302
RÉSISTANCE THERMIQUE	0.15 m ² K/W
WÄRMEDURCHLASSWIDERSTAND	
WARMTEDOORLAATWEERSTAND	
FASTNESS TO LIGHT	ISO 105-B02
SOLIDITÉ A LA LUMIÈRE	≥ 5-6
LICHTECHTHEIT	
LICHTECHTHEID	
COLOUR FASTNESS TO WATER	EN ISO 105-E01
SOLIDITÉ À L'EAU	≥ 4-5
WASSERRECHTHEIT	
WATERECHTHEID	
FIRE RESISTANCE	EN 13501-1
COMPORTEMENT AU FEU	Bfl-s1 (if glued)
BRENNVERHALTEN	
BRANDGEDRAG	
RUBBING FASTNESS	EN ISO 105-X12
SOLIDITÉ AU FROTTEMENT	≥ 4
REIBECHTHEIT	
WRIJFECHTHEID	
WIDTH	EN ISO 3018
LARGEUR	ca. 400 cm
BREITE	
BREEDTE	





TUV NORD
Systems
Primary Material Test
According to EN ISO 9001


Suitable for Allergic Persons
Wait to wait carpet of allergen-tested material
3.2-2384/05
























EN14041

16


Balta Industries - Kanegem-
straat 15 - BE 8700 Tielt

DOP: 1011#IE0ABV

Textile Floor Covering EN1307
Notified body 2401




www.baltamediabank.com



UPEC
moquettes touffetées et tissées en lés
<http://evaluation.cstb.fr>

REG. NR
1721C645
www.pro-dis.info





↔ 24 X ↕ 24 CM

39



95




49



47



10



23



77

